


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A46B 9/04, A61C 17/00	A1	(11) International Publication Number: WO 98/04167 (43) International Publication Date: 5 February 1998 (05.02.98)
(21) International Application Number: PCT/US97/12206 (22) International Filing Date: 24 July 1997 (24.07.97) (30) Priority Data: 60/022,601 25 July 1996 (25.07.96) US (71) Applicant: WHITEHILL ORAL TECHNOLOGIES, INC. [US/US]; 1349 Hillendale Road, Chadds Ford, PA 19317 (US). (71)(72) Applicant and Inventor: SCHIFF, Thomas [US/US]; 24 Lyford Drive, Tiburon, CA 94920 (US). (72) Inventor: HILL, Ira, D.; 10 Clay Court, Locust, NJ 07760 (US). (74) Agents: LINEK, Ernest, V. et al.; Dike, Bronstein, Roberts & Cushman, LLP, 130 Water Street, Boston, MA 02109 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: TOOTHBRUSH WITH IMPROVED CLEANING AND ABRASION EFFICIENCY**(57) Abstract**

A toothbrush having a plurality of bristles (12) of synthetic thermoplastic polymeric composition. The bristles (12) having a plurality of channels (13) therein extending along the length thereof. The channels (13) having a depth sufficient to entrap a quantity of toothpaste abrasive, wherein the cleaning and abrasion contact between the quantity of abrasive entrapped in the channels (13) and the surfaces of the teeth is improved during brushing.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		

- 1 -

TOOTHBRUSH WITH IMPROVED CLEANING AND ABRASION EFFICIENCY

FIELD OF THE INVENTION

A toothbrush having an improved cleaning and abrasion efficiency, wherein the bristles are comprised of synthetic thermoplastic polymeric compositions, and contain longitudinal channels extending along the length thereof, having a depth sufficient to entrap a quantity of abrasive particles such that during brushing with an
5 abrasive toothpaste, contact between the channel entrapped abrasive particles and the surfaces of the teeth is improved, resulting in a cleaning efficiency coefficient, CEC, above about 1.5 and, an abrasion efficiency coefficient, AEC, above about 1.5 while demonstrating suitable bristle wearability.

10 BACKGROUND OF THE INVENTION

The present invention relates to a toothbrush having improved cleaning and abrasion efficiency while retaining acceptable wear characteristics.

15 In the oral hygiene field today, toothbrushing is ordinarily accomplished with a toothbrush which is adapted for use with a dentifrice composition, i.e., a toothpaste, which contains an abrasive substance or material designed to abrasively clean the teeth, i.e., to remove materials thereon, including pellicle, plaque, stains, dental calculus (tartar), and the like.

- 2 -

The current level of gum disease and tooth loss attributed to gum disease and gum retraction in adults, along with the incidence of gingivitis among adults, is an indication of the inefficiency of cleansing accomplished with those toothpaste/toothbrush combinations presently commercially available. In part, this
5 poor cleaning is also due to the poor toothbrushing habits of a majority of adults which include; brushing only once a day, brushing improperly, and/or failing to brush long enough to effect adequate plaque, tartar removal, etc. Clearly, a more efficient toothbrush/toothpaste combination would be helpful.

10 In toothbrushing, the primary function of the bristle is to rub abrasive particles across the surface of the teeth and thereby remove by abrasive action deposits such as pellicle, stains, plaque, tartar and the like from tooth surfaces.

Accordingly, the tangential contact between toothpaste abrasive and surfaces
15 of the teeth as influenced by toothbrush bristle tips during brushing has a major impact on toothbrushing efficiency.

Manufacturers of nylon bristle toothbrushes have provided in the past, a variety of toothbrushes designated as "soft," "medium," and/or "hard" to indicate the stiffness of the bristles. For a given thermoplastic polymeric composition, one factor,
20 which predominantly determines bristle stiffness, is the diameter of the individual bristles. For example, with nylon 6,12 the "soft" bristles typically have a diameter between 0.008 and 0.009 inches; "medium" bristles have a diameter between 0.009 and 0.012 inches and "hard" bristles have a diameter greater than about 0.012 inches.
25 Polybutylene terephthalate bristles are typically about 0.001 to 0.002 inches smaller in diameter due to the greater wet stiffness of this material over that of nylon 6,12. For all bristles used in toothbrushes, there is generally a manufacturing or grading tolerance of about ± 0.0005 inches.

30 Soft bristles penetrate crevices between the teeth, while medium bristles and

- 3 -

the hard bristles stabilize the soft bristles against bending as pressure is applied during brushing. The medium and hard bristles are believed to more effectively clean the surfaces of the teeth while the soft bristles achieve better penetration of crevices and are recommended for their gentleness to soft tissue.

5

Studies have shown that the most aggressive mechanical cleansing should be directed toward the tooth surface, with much less so toward the gingival surface and essentially none toward the base of the gingival sulcus. The basis for these observations is as follows:

10

1. The development of gingival inflammation and dental caries is most frequently caused by failure to remove dental plaque from the subgingival surface of the tooth and to a much lesser extent *materia alba* from the gingival surface in the subgingival space. Both dental plaque and *materia alba* can form within several hours of brushing and therefore frequent mechanical cleansing is essential. *Materia alba*, which consists primarily of an acquired bacterial coating and desquamated epithelial cells, leukocytes and a mixture of salivary proteins and lipids, is a soft sticky deposit less adherent than dental plaque. It can be flushed away with a water spray but more completely removed from the gingiva with mild mechanical cleansing.

15

20

2. Dental plaque is formed by oral microorganisms that synthesize harmful products that are destructive to the tooth and gums when not removed from the gingival sulcus. The toxins formed by these microorganisms cause cellular damage to the gingiva with subsequent inflammation (gingivitis) and eventually destruction of the supporting structures (periodontitis). When gingivitis occurs, vascular dilation, capillary proliferation, engorged vessels and sluggish venous return causes a stretched and thinned epithelium that is sensitive to mechanical trauma such as aggressive brushing.

25

30

3. Dental plaque with associated gingivitis also causes exposure of the

- 4 -

- 5 root surface (recession) with increased occurrence of cavities (dental caries). Exposure of the root surfaces can also occur due to faulty brushing by repeated direct trauma to the base of the sulcus (gingival abrasion). When a pathologically deepened gingival sulcus (periodontal pocket) occurs, the pathological condition may become exacerbated because plaque can more readily occur. If dental plaque is not removed, calculus (tartar) is formed by mineralization of the bacterial plaque. Calculus can form within several hours of plaque formation. Calculus has a bacterial plaque coating and exacerbates gingivitis and gingival recession by both chemical irritation from the formed toxins and destruction from the mechanical irritation of the calculus mass. Subgingival calculus usually extends near but does not reach the base of periodontal pockets in chronic periodontal lesions. Calculus holds the plaque against the gingiva, and
- 10
- 15 4. Since *materia alba* can be removed by light mechanical cleansing and gingival inflammation causes thinning of the gingival epithelium the mechanical cleansing requirement of the gingival surface is much less than the requirement for removing dental plaque from the surface of the teeth.
- 20 Accordingly, a more efficient cleansing and abrading toothbrush, which fulfills the foregoing requirements while protecting the base of the gingival sulcus, is desirable.

Review of Prior Art

- 25 Toothbrush bristles have come a long way from the curly-tusked swine hair they were made from prior to World War II. First was the introduction of nylon synthetic fiber in 1938. The popular round toothbrush bristle style introduced in 1938 is used today in more than 50% of the premium toothbrushes used worldwide.

- 5 -

Since 1938 nearly all major toothbrush marketers have developed innovative "cosmetic" features which make their toothbrush offerings unique at the retail shelf. These features included: colors, packaging, innovative handle and head designs, trimming alternatives, various tufting arrangements, various bristle lengths, bristle
5 diameters, etc. Whatever the cosmetic feature(s) promoted, these commercial toothbrushes have typically relied on the basic cylindrical bristle with rounded tips for abrasive/tooth surface contact. See for example, U.S. Patent Nos. 3,217,074, 4,898,193, 4,927,281, 4,993,440, 5,020,552 and 5,511,275.

10 Recently, unique bristle designs have been designed and commercialized reportedly to improve plaque removal, interdental cleaning, gum care and durability. All of these recent innovations also rely on the classic bristle tip (usually rounded) abrasive contact with the tooth surface to affect cleaning. See Tynex® *Shapes and Textures Toothbrush Filaments* "... because specialized cleaning starts at the tips" (H-
15 50102) published by the DuPont Company, Washington WV 26181, 1995. This publication is hereby incorporated herein by reference.

Summarized below in Table 1 are some recent industry approaches to various consumer toothbrush needs where toothbrush bristle shape, and texture are varied to
20 provide "specializing cleaning". Note: These approaches are based on bristle tip/toothpaste abrasive interaction to achieve cleansing and abrasion of tooth surfaces.

- 6 -

Table 1

Consumer Need	Feature to Address Consumer Need	Recommended Tynex® Bristle Construction
Interdental Cleaning	Fine tips able to reach farther between teeth. More bristles per tuft working with every stroke.	Feathered Hexagonal
Plaque Removal	Higher surface contact area increased ability to hold toothpaste at tips. Higher functional abrasiveness. Compliance with Bass brushing Methods.	Hexagonal Feathered Grainy, Co-Extruded Rectangular
Healthy Gums	Gentleness to the gums End-rounded tips More surface area to distribute force applied to brush Softness of tips	Feathered, Rectangular All styles Hexagonal Feathered
Durability	Improved Wear Technology Superior bristle integrity	All Styles Hexagonal

- 7 -

Various cross-sectional geometric bristle shapes have been developed to enhance the performance of toothbrushes in general. For example, U.S. Patent No. 2,317,485 teaches that circular cross-sectional bristles do not pack as efficiently as other shapes such as triangles, squares, pentagon's etc. U.S. Patent No. 2,876,477
5 utilizes polygons with a concave contour on each side to maximize interstitial spacing. The corners of the bristle sides serve as scrapers for the bristles. The multi-fluted sides of these bristles are designed to function in a manner analogous to scaly natural bristles.

10 Bristle brushes other than toothbrushes with various cross-sectional shapes are disclosed in U.S. Patent Nos. 4,386,325; 4,898,193; 4,167,794, 5,020,551 and 5,396,678. U.S. Patent No. 5,396,678 teaches toothbrush bristles having a rectangular cross-sectional shape. U.S. Patent No. 5,020,551 discloses various bristle cross sections including: solid circular, hollow circular, cruciform, and multilobal.
15 U.S. Patent No. 4,898,193 teaches multi-ridged polygon bristles for combing eyelashes and for applying mascara to the eyelashes. This reference teaches that the sides of the polygon bristle can curve inwardly. Similarly U.S. Patent No. 4,381,325 discloses a liquid-retaining synthetic bristle having an acute ridgeline extending longitudinal on its surface. The bristle has at least one convex portion. The arcuate
20 concave grooves were shown to retain more liquids such as India ink than non-ridged comparable brushes.

U.S. Patent No. 3,613,143 discloses toothbrushes with abrasive impregnated bristles of two cross-section designs, i.e., generally circular and polygon with the
25 latter described as having longitudinal groove arrangements.

U.S. Patent No. 4,167,794 discloses rounded bristles having shovel-like distal ends for more effective plaque removal.

30 U.S. 4,958,402 teaches fiber-flocking synthetic bristles as a means of

- 8 -

retaining the substance to be applied and more effectively distributing the substance on the surface to be treated. These fiber-coated bristles are taught for use in interdental cleaning. Similarly, U.S. Patent No. 5,195,546 teaches having a gentle random and irregular wavy configuration along the length of the bristles for the improved application of powder to surfaces.

U.S. Patent No. 2,312,828 teaches improved abrasive tooth surface contact by forming in the working face of the brush a longitudinal groove or channel of a size to receive and hold a strip of paste squeezed from the tube, this groove or channel being completely closed at its sides and ends by the outside longitudinal and transverse rows of full length bristles, so that the paste or powder deposits cannot fall from the brush.

U.S. Patent No. 2,599,191 teaches improved toothbrushes for treating gum disease where the bristles are looped resulting in a smooth "side surface" contact with teeth and soft tissue.

U.S. Patent No. 2,845,649 teaches a small diameter nylon bristle with higher tuft count produces a "sweeping action" as distinguished from traditionally "coarse" toothbrushes. It is suggested this sweeping action is gentler on soft tissue.

U.S. Patent No. 4,993,440 describes a brush for the application of cosmetic products such as mascara, where the bristle has a capillary channel extending from the base to the tip. This channel has a V-shaped or U-shaped cross section designed to hold the mascara.

Toothbrush constructions of various types have been disclosed throughout the prior art to accommodate access to various components of an individual's mouth during a toothbrushing procedure. Such toothbrushes are exemplified in U.S. Patent No. 4,800,608 wherein the bristle head is formed having a fixed obtuse angle. See

- 9 -

also U.S. Patent Nos. 3,072,944; 3,188,643; 3,263,258; 5,346,678; 5,274,873;
5,335,384; 5,355,546; 5,360,025; 5,497,526 and 5,511,275.

U.S. Patent No. 4,729,142 sets forth a toothbrush head having the bristles
5 directed towards the medial center of the toothbrush head.

U.S. Patent No. 4,852,202 sets forth a toothbrush head having angulated
bristles, wherein the bristles include first bristles having an orthogonal orientation
relative to the toothbrush head, with a plurality of secondary bristles mounted at a
10 generally forty-five degree angle relative to the toothbrush head.

U.S. Patent No. 3,032,230 teaches bristles with a polygon cross-section
having at least two acute angles that impart a "scraping" effect on the teeth. U.S.
Patent No. 3,214,777 teaches bristles with a rectangular cross-sectional area.
15

See also U.S. Patent Nos. 2,088,839; 3,295,156; 3,722,020; 3,939,520;
4,167,794; 3,217,074; 3,238,553 and 4,927,281.

The prior art also teaches that generally, most adult toothbrushes have
20 between 2000 and 3000 bristles with between 2300 and 2600 most popular. These
bristles are usually arranged in three to five rows with about 15 tufts/row. In
contrast, a child's toothbrush may have only three rows with approximately 10 tufts
in each row.

25 Until the present invention, all toothbrush bristle constructions described in
the prior art, including round, round/hollow, multi-lobal, rectangular, hexagonal, etc.
type bristles could be characterized as effecting only tangential "point" contact
between the bristle tip, the abrasive, and the surface. The present invention
represents the next advance in this area, providing greater contact between these
30 elements.

- 10 -

OBJECTIVES

The present invention thus has as its primary objective the enhancement of tooth cleaning and polishing through improved cleaning and/or abrasion efficiency wherein contact between cleaning abrasives and the toothbrushes of the present invention improve tooth surfaces. The improvement in cleaning efficiency is measured by a Cleaning Efficiency Coefficient, CEC, which is defined below. The improvement in abrasion efficiency is measured by an Abrasion Efficiency Coefficient, AEC, which is also defined below.

10

Another object of the present invention is to efficiently remove plaque and tartar and to provide a smooth tooth surface resistant to plaque and tartar buildup by enhancing the contact between abrasives and tooth surfaces with the improved toothbrushes of the present invention, wherein the abrasive is contained in a toothpaste also having a plaque buildup fighting, active ingredient that coats the freshly cleaned tooth surface with a poloxamer polydimethyl-siloxane emulsion containing coating during the toothbrushing.

15

A further objective of the present invention is to enhance the cleaning of those tooth surfaces contiguous to the gingival margin and to interproximal surfaces by improving the contact between the abrasives in toothpaste and these various critical surfaces of the teeth by the toothbrush bristles of the present invention, whereby entrapped abrasive is delivered to these critical tooth surface areas during brushing in a manner sufficient to remove plaque, stains and tartar while depositing coating substances that help fight plaque and tartar buildup.

20

25

A still further object of the invention is to improve the tooth cleaning performance of the majority of toothbrushes who: (a) routinely fail to brush for a long enough period of time, i.e., 20 to 30 seconds vs. two minutes (as recommended by the American Dental Association, ADA); (b) fail to brush frequently, i.e., about

30

- 11 -

once a day, vs. preferably after every meal and/or snack; and (c) brush with an improper brushing motion on most lingual and buccal surfaces vs. the recommended Bass Method of brushing.

5 Yet another object of the invention is to manufacture a toothbrush with improved cleaning efficiency coefficient, CEC, of at least about 1.5, along with an improved abrasion efficiency coefficient, AEC, of at least about 1.5 (as defined below).

10 Another object of the invention is to provide a means for efficiently cleaning and polishing hard oral surfaces while avoiding injuring the soft tissue.

 A further object of the invention is to adapt the channeled, abrasive entrapping bristles, of the present invention to the various heads of commercial
15 toothbrush innovations such as described in U.S. Patent Nos. 3,072,944; 3,188,673; 3,262,258; 5,274,873; 5,396,678; 5,335,389; 5,355,546; 5,360,025; 5,401,526; and 5,511,275.

 Another object of the invention is to adapt the channeled, abrasive entrapping
20 bristled toothbrushes of the present invention to the various commercial toothpastes, including those described in U.S. Patent Nos. 4,254,101; 4,515,772; 4,999,184; 4,842,165; 4,684,518; 4,885,155; 4,806,339; 5,004,597; 4,806,340; 4,889,712; 4,925,654; 4,591,211; 5,374,368; 5,424,060 and 5,180,576.

25 Yet another object of the invention is to provide an improved method of caring for the teeth and gums using a toothpaste containing an active ingredient that fights plaque buildup.

- 12 -

SUMMARY OF THE INVENTION

The foregoing and other objects, advantages and features of the present invention are achieved through the use of toothbrushes with novel bristle construction, such as those illustrated in Figs. 1-4. The present invention provides a more efficient toothbrush that has ribs and/or grooves on the bristle periphery. These ribs and grooves are sized and arranged as to trap and hold the toothpaste abrasives and other active ingredients against the teeth and soft tissue surfaces of the mouth more effectively than previously known brush designs.

10

In the preferred embodiments of this invention, the abrasive and/or tubule closing ingredients contained in various toothpastes are entrapped in longitudinal channels formed in the toothbrush bristles. During brushing these channel-entrapped-abrasives and tubule closing substances are brought into functional contact with tooth surfaces, resulting in improved cleaning efficiency and/or improved treatment of hypersensitivity. This is illustrated in Figs. 6 and 7. The improved cleaning efficiency is measured by a Cleaning Efficiency Coefficient, CEC, as defined below, as is the improved Abrasion Efficiency Coefficient, AEC.

Specifically, the Cleaning Efficiency Coefficient (CEC) is a number which relates the cleaning efficiency of the novel toothbrush bristle construction to current standard round bristle construction, where both bristle types are tested in an identical head design and tuft placement. One advantage of such a Coefficient is the ability to compare complex variables, using multiple measures of cleaning. For example, such a coefficient is useful in comparing *in vitro* removal of artificial plaque, food debris, *materia alba*, etc. It is equally useful in correlating *in vivo* measurements on plaque and tartar removal or other clinical indications.

The CEC is a ratio of the efficiency of the test bristle to the efficiency of a standard round bristle under standardized use conditions. The ratio is expressed as the reduction in the parameter measured (plaque, for example) by the test bristle in

- 13 -

any specific configuration, divided by the reduction in plaque produced by standard round bristles under identical toothbrush design and test conditions. See Example 1 and Table 4 below. This relationship may be expressed as follows:

$$\text{CEC} = \frac{\text{Baseline}_{\text{Test}} - \text{Final}_{\text{Test}}}{\text{Baseline}_{\text{Std. Round}} - \text{Final}_{\text{Std. Round}}}$$

"Cleaning Efficiency Coefficient" (or CEC), as noted above is an indicator of the cleaning improvement obtained with the toothbrushes of the present invention, as measured against a standard comprising a toothbrush with bristles of a circular cross-section, with both toothbrushes using the same abrasive containing toothpaste under standard brushing conditions. The CEC observed after crossover clinical testing, such as described in Example 1, and reported in Fig. 8 and in Table 4, is 2.5%. For purposes of the present invention, CEC values greater than about 1.5 are preferred. Particularly preferred are CEC values above about 2.0.

The unexpected improvement in cleaning efficiency as reported in Example 1 for the quadrachannel bristled toothbrush of the present invention, can also be expected for various other multi-channel bristle configurations such as those described in Tables 2 and 5 and illustrated in Figures 2-4 of the drawings. Improvements in AEC are also expected.

In addition to the above reported, yet unexpected and dramatic improvement in clinical cleaning efficiency observations, it has been further found that significant improvement in abrasive cleaning efficiency is achieved with the present invention, without incurring an observable adverse effect on the "soft tissue" contiguous to the teeth. In part this favorable tooth/soft tissue cleaning result is attributed to the "softer" bristles used in the toothbrushes of the present invention and to the efficient abrasive/tooth contact effected by the multi-channeled bristles of the present

- 15 -

of a series of abrasives having varying particle sizes, compositions of matter, crystal structures, fracture edges, etc. Typically a measured number of strokes with a standard toothbrush with a fixed applied pressure against a piece of dental enamel fixed in a holding plate is the basis of the test. Sometimes a plate of soft metal, such as copper, is substituted for the dental enamel as an inexpensive approximation method. The dental enamel is measured for loss of surface enamel (or metal) by a variety of methods, including weight loss, optical comparison and radioactive techniques.

10 A similar measurement using artificially stained enamel measures the abrasive removal of stain. In a similar fashion, one can evaluate the polishing of tooth surfaces, a process which increases the reflectance properties of the enamel without a high level of enamel removal or "scratching".

15 As long as the brush, its bristles, and the mechanical parameters are constant, the RDA (and its Stain Index and Polishing Index counterparts) has proven to be the most useful tool available to the toothpaste formulate. For the toothbrush designer using only round bristles of a given softness/hardness property, the RDA is of a lesser value in predicting *in vivo* performance, even if the abrasive formulation is kept constant, since bristle positioning has only modest impact on the abrasive properties of the chosen abrasive.

25 In the present invention, the changing of the bristle design according to the present specification impacts the abrasivity, both absolute and relative, of differing abrasives and formulations to a much greater extent. Therefore, to effectively appreciate and evaluate the advances of the present invention, it is necessary to modify the standard RDA and create a new measurement technique called the Abrasion Efficiency Coefficient (AEC).

30 It is self-evident that because the entrapment and resulting delivery of the

- 16 -

abrasive agent to the tooth surface is more efficient as a result of this invention, certain abrasives (especially those with very high relative hardness or sharp crystal edges) will have a higher RDA when applied with these brushes.

5 Conversely, if a "non-scratching" abrasive is more effectively delivered, it can do a more complete job of removing plaque, or even polishing, without having to possess a high RDA. The advantage of this performance is obvious in that the teeth are more effectively cleaned, both clinically and cosmetically, without resort to the extent of enamel damage previously demonstrated with high RDA abrasive systems.

10

 The longitudinal channel feature of the bristles of the present invention shown in Figs. 1-4 requires a bristle core of sufficient diameter and strength to achieve:

- 15 a) strength/stiffness values and
 b) bend recovery/wear values

such that the wearability of the toothbrushes of the present invention are comparable to commercially available toothbrushes with traditional bristle construction.

20 Were these strength/stiffness and bend recovery/wear values not factored into the channeled bristle designs of the present invention, the toothbrushes of the present invention would fall far short of conventional toothbrushes in the critical area of wearability.

25 The multi-channeled bristles of the present invention not only provide a substantial improvement in abrasive/tooth surface contact, attributed to entrapment of effective quantities of abrasive in the channels during brushing, but, in one embodiment of the invention, they also provide a unique interlocking bristle feature. That is, certain bristles of the present invention during brushing tend to interlock,
30 resulting in less open space between bristles effecting a more contiguous contact with

- 17 -

tooth surfaces, resulting in optimum CEC and AEC values. This interlocking of the channeled bristles of the present invention is best illustrated in Figures 5, 7 and 11(a) of the drawings.

5 Generally, the bristles of the present invention have sides more adaptable to interlocking and accordingly are readily distinguished from their round cross-section counterparts. As a result, toothbrushes of the present invention, with "interlocking" during brushing produce higher CEC and AEC values than other toothbrushes.

10 As described in greater detail below, the present invention is based upon the clinical observations that:

1. Best toothbrush action is accomplished by the "sides" of the bristles, rather than by the tips of the bristles. (see Figures 6 and 7)
- 15 2. Conventional bristles in combination with abrasive particles effect minimal "bristle driven abrasive cleaning action" during brushing.
3. During toothbrushing the bristles "flex" whereby the sides of the bristles rather than the tips become the "primary cleaning contact" area of the toothbrush with the surfaces of the teeth, (see Figures 6 and 7), and
- 20 4. Means for entrapping abrasive in the sides of toothbrush bristles will improve abrasive/tooth surface contact and cleaning efficiency of the toothbrush.

 The current state of the art for toothbrush manufacturing emphasizes that: "superb end-rounding (of bristles) enhances gentleness to the gum line area" (see
25 Tynex® reference, *supra*). The present invention suggests that channeled bristles entrapping abrasive producing improved CEC and AEC values assures gentleness to the gum line area, that can be clinically substantiated.

 End-rounding the bristle tips of the present invention although doable, (See
30 Figures 9 & 10) is not required for achieving comfort along the gum line and

- 18 -

avoiding damage to the delicate gum tissue. That is, the overall softness of the bristles of the present invention in combination with the "flagging" achieved with the multi-channeled bristle tips of the present invention reduces the necessity of end-rounding these bristles. "Flagging" is discussed in detail below. The bristles of
5 the present invention are generally perceived as softer and gentler on gums than most and rounded commercial bristles. The improved CEC and AEC performance of the brushes of the present invention reduces the brushing force required to achieve cleaning, thereby obviating damage to gum surfaces.

10 Toothbrushes of the present invention are particularly complementary of the dentist recommended Bass Method for brushing teeth. The Bass Method calls for up and down strokes on the sides of the teeth with back and forth strokes on the tops of teeth. The multi-channeled bristles of the present invention with their entrapped abrasive assure improved abrasive tooth surface contact with both "up and down" as
15 well as "back and forth" strokes of the toothbrush. As a result, effective abrasion cleaning is achieved on the tops of the teeth while soft gentle thorough abrasion cleaning is effected on the sides of the teeth. This entrapped abrasive cleaning of the tops of the teeth and the sides of the teeth is schematically illustrated in Figs. 6 and 7.

20 It is generally recognized in the art that non-round bristles (which would include the unique multi-channeled bristles of the present invention) provide substantially more softness than comparable round cross-section bristles when brushing the teeth with up and down strokes. (See Tynex® reference, *supra*). It is suggested that, this softness combined with the inherent gentleness on gums reported
25 for the bristles of the present invention should help reduce gum retraction due to toothbrushing.

Historically, toothbrushing based gum retraction has been considered a major reason for tooth loss along with gum disease. The toothbrushes of the present
30 invention with their "flagged" tips, and improved CEC and AEC values, promise to

- 19 -

minimize toothbrushing based gum retraction, as detailed below.

The multi-channeled bristles of the present invention are particularly adaptable to splitting at the ends, i.e. "flagging", producing soft fine strands or "feathers" that have been reported to affect efficient interdental and gum cleaning while still being gentle on gums. These "feathers" at the tips of the bristles offer outstanding clinical benefits including:

- (a) Higher contact surface area for the bristle tip which in combination with the channel entrapped abrasive affects unexpectedly improved cleaning efficiency, CEC;
- (b) Superior plaque removal without damaging the gum: These soft multi-channeled bristles with feathered tips have the ability to reach further between teeth and gum line areas to enhance interdental and gum line cleaning; and
- (c) Superior cushion effect on the gums as perceived by subjects and generally described as "gentle on gums" during clinicals.

"Flagging" is described in U.S. Patent Nos. 2,697,009, 2,911,761, 3,295,156, and 5,128,208, the disclosures of which are hereby incorporated herein by reference.

In a preferred embodiment of the invention, as illustrated in Figures 1 and 5-7, the toothbrush bristles contain longitudinal cavities such as channels extending along the length thereof having a depth sufficient to entrap abrasives having a particle size between about 3 and about 25 microns and preferably between about 6 and about 20 microns. Figs. 2 and 3 illustrate various cross-sectional configurations of preferred abrasive entrapping bristles of the invention.

In another embodiment of the invention, the toothbrushes of the present

- 20 -

invention are combined with toothpastes that also contain active ingredients that fight plaque buildup to provide an improved method of brushing teeth. This combination results in teeth with improved CEC and AEC scores that surprisingly also exhibit an improvement in fighting plaque buildup.

5

In a specific embodiment of the invention the combination of the toothbrushes of the present invention with certain toothpastes, in addition to providing improved cleaning and abrasion of the teeth, including improved plaque removal, unexpectedly produce a surprising reduction in plaque buildup. That is, when the toothbrushes of the present invention are used with toothpastes containing MICRODENT®
10 ULTRAMULSION® an unexpected method of reducing plaque buildup is also obtained. Such toothpastes are disclosed in U.S. Application Serial No. 08/461,698, filed June 5, 1995, now U.S. Patent No. _____. Other preferred toothpaste compositions are disclosed in U.S. Application Serial No.
15 _____, Attorney Docket No. 1648/46678, filed on even date herewith. The contents of these two applications are hereby incorporated herein by reference.

It appears the improved cleaning and abrasion obtained by the
20 channel-entrapped abrasives contacting the tooth surfaces provides optimum tooth surface preparation which is then followed up by a coating of tooth surfaces with MICRODENT® ULTRAMULSION®.

When a toothpaste containing MICRODENT® ULTRAMULSION® is used,
25 those tooth surfaces that have been cleaned with the toothbrushes of the invention generally indicate a most thorough, consistent and effective coating that is well suited to resisting plaque buildup.

Specific preferred embodiments of abrasive entrapping bristles according to
30 the present invention will now be described with reference to the accompanying

- 21 -

drawings. In the description that follows, specific bristle constructions will be used for purposes of clarity, but these are not intended to define or to limit the scope of the invention, which is defined solely in the claims.

5

BRIEF DESCRIPTION OF THE DRAWINGS

Figs. 1A and 1B are schematic side views illustrating a 0.012 inch cross-section bristle embodying an abrasive entrapping channel of the invention, wherein the channel depth is about 0.003 and the channel breadth is about 0.006.

10

In Fig. 1A the bristle channel is shaded in order to accentuate the abrasive entrapping feature to be described hereafter.

15 Figs. 2A, B and C represent the present invention various tri-channeled cross-sectional bristle shapes applicable to the improved Cleaning Efficiency Coefficient (CEC) and Abrasion Efficiency Coefficient (AEC) toothbrush of the present invention.

20 Figs. 3A, B and C represents various quadra-channeled cross-sectional bristle shapes with various "channeling" suitable for the improved Cleaning Efficiency Coefficient (CEC) and Abrasion Efficiency Coefficient (AEC) toothbrush of the present invention.

25 Fig. 4A, B and C represent various poly-channel cross-sectional bristle shapes with various channeled bristles suitable for delivering the CEC and REC values of the present invention.

Fig. 5 is a perspective plan view of a toothbrush tuft of the present invention illustrating the tuft arrangement of one of the bristles of the present invention.

30

- 22 -

Fig. 6 illustrates schematically, the general contact between the channeled bristles of the present invention containing entrapped abrasive, and the tooth surface, during brushing.

5 Fig. 7 illustrates schematically a magnified view of the contact between bristle-channel-entrapped abrasives and interproximal surfaces of the teeth during brushing with an abrasive containing toothpaste.

10 Fig. 8 is a bar chart that compares the average plaque scores for a quadra-channeled bristle toothbrush of the present invention compared to a toothbrush with round bristle configuration when both are used in a crossover clinical study, with a common commercial toothpaste, as described in detail in Example 1.

15 Figs. 9 and 10 are electron microphotographs of tips of toothbrush bristles of the present invention, and a conventional round toothbrush bristle tips.

20 Figs. 11(a) illustrates schematically a magnified view of a cross-section of the "packing" of one of the bristles of the invention into a tuft with the bristle interlocking feature of the present invention (11A) compared to the cross-section packing of rounded bristles into a tuft Fig. 11 (b).

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

25 For the purposes of the present invention, multi-sided channeled bristles are defined as toothbrush bristles that have been formed in a multi-channeled cross-section shape, wherein at least three, preferably four, most preferably five like-shaped individual channels are provided at the lower (i.e., tip) end of each bristle. The individual channels are thus capable of entrapping appreciable quantities of abrasive particles during brushing with a toothpaste, and the entrapped abrasive particles will
30 be delivered to the surface of the teeth with a force sufficient to affect improved

- 23 -

cleaning and abrasion efficiency, while avoiding abrasion of the enamel dentin and while avoiding adversely affecting the soft tissue.

For the purposes of the present invention, a "channel" is defined as a
5 depression, hollow or cavity, which preferably extends the entire length of each
bristle, wherein the cavity is of sufficient depth to accommodate sufficient toothpaste
abrasive such that the entrapped abrasive is delivered to the tooth surface during
brushing with a force from the channeled bristle sufficient to effect a Cleaning
Efficiency Coefficient (CEC), of at least about 1.5, and an Abrasion Efficiency
10 Coefficient (AEC), of at least about 1.5.

In one preferred bristle dimension of 0.012 inches in diameter as shown in
Fig. 1, the preferred channel is about 0.013 inches deep with a breadth of about 0.006
inches. See also Figs. 2-7 and 11(a) and Tables 2, 3 and 5. The dimensions of the
15 channels are described in various Examples as set forth below. For example, at
bristle diameters ranging from between about 0.008 and about 0.014 inches, channel
depths from between about 0.007 and 0.005 inches are disclosed along with a channel
breadth ranging from between about 0.003 and 0.006 inches. It is understood that for
larger diameter bristles these channel depth and breadth values may increase
20 substantially.

For the purposes of the present invention a toothbrush is defined as any
manual, interproximal, or mechanical toothbrush containing multiple tufts of
thermoplastic polymeric bristles, and specifically includes the various commercially
25 available toothbrush handles and head designs popular today, as well as the various
tuft arrangements, bristle variations, including various lengths of bristles and bristle
bundle packs. These toothbrushes are marketed in the U.S. under trademarks
including: Braun®, Interplak®, Oral-B®, Complete®, Precision®, Total®,
REACH®, MentaDent®, IUM™, Gum®, InterPlak®, Oral Logic, etc. Various
30 toothbrushes as described in the following U.S. Patents are suitable for adaptation of

- 24 -

the bristles of the present invention: 3,072,944, 3,188,673, 3,263,258, 5,396,678, 5,274,873, 5,335,389, 5,355,546, 5,360,025, 5,497,526, and 5,511,275. The teachings of these references are to be included in this specification by reference.

5 Suitable bristles of this invention having various cross- sectional shapes are illustrated in Figs. 2 through 4 and discussed in detail in Tables 2-5 below.

Referring now to Figures 6 and 7, the channel entrapped abrasive 10, is brought into contact with the various surfaces of the teeth 11 by bristle 12 in a wiping
10 mechanism of action. In other words, upon flexing of bristle 12, bristle channel 13 achieves extended abrasive/tooth surface contact as illustrated at 6 and 7. In the wiping action, this surface contact is maintained between the bristle channel 13 and the tooth surface.

15 The polymers useful with the bristles of the present invention may be prepared by methods now well know in the art such as the procedures described by G. Notta in the *Journal of Polymer Science*, Vol. XVI. pp. 143 to 154 (1955) and in U.S. Patent Nos. 2,882,263; 2,874,153; 2,913,442; 3,112,300 and 3,112,301 the disclosures of which are hereby incorporated herein by reference.

20 The bristles may be formed by melt extruding various thermoplastic polymeric materials through appropriately shaped extrusion orifices in various dies following various processes such as described in U.S. Patent Nos. 2,226,529 and 2,418,482; 3,745,061; 3,238,553; 3,595,952; 4,279,053; French Patent No.
25 2,125,920, and European Patent Appln. No. 0663162171.

The tufting, cutting, stapling, etc., of the bristles is performed by processes known in the art; for instance as described in U.S. Patent Nos. 4,441,227; 4,688,857; 979,782; 5,274,873; 5,335,389; and 5,511,275, the disclosures of which are hereby
30 incorporated herein by reference.

- 25 -

For the purposes of the present invention, thermoplastic polymeric compositions suitable for the bristles of the present invention include synthetic linear condensation polyamides, such as described in U.S. Patent Nos. 2,071,250,
5 2,071,251, 2,130,948 and 3,671,381.

The synthetic polyamides useful in the bristles of the present invention includes those which are of sufficient molecular weight to be fiber-forming such as: polycaprolactam, polyhexamethylene adipamide, polyhexamethylene sebacamide, the
10 polyamide formed from 1,4,(cis)cyclohexane-bis(methylamine) and adipic acid (see U.S. 3,012,994); the polyamide from m-xylene diamine and adipic acid (see U.S. 2,916,475); the polyamide from 3,5 dimethyl hexamethylene diamine and terephthalic acid (see U.S. 2,752,358); the polyamide from 2,5 dimethyl piperazine and adipyl chloride (see U.S. 3,143,527). See also U.S. 2,152,606. The preferred
15 polyamides are polyhexamethylene adipamide; and polyhexamethylene sebacamide.

In general, the number average molecular weight of the polymer used for these bristles should be in excess of 10,000 and preferably greater than 30,000 to provide the strength and stiffness needed in a toothbrush bristle. The commercial
20 polyamides preferred include nylon 6,6; nylon 6,10 and nylon 6,12. Of these nylon 6,10 (polyhexamethylene sebacamide) and nylon 6,12 (hexamethylene diamine are particularly preferred. See Table 2.

Polyesters that have been found particularly well suited to the bristles of the
25 present invention include polybutylene terephthalate and polyethylene terephthalate. (See Tables 3 and 5 below).

The overall diameter, or maximum cross-section for the bristles of the present invention can be between about 4 and 20 mils. Bristles outside this range, in general,
30 will exhibit stiffness, which is unsuitable for toothbrush bristle applications of the

- 26 -

invention. The bristles generally extend from between about 8 and 15 mm above the toothbrush head.

5 It is known that bristles of thermoplastic materials may have their properties enhanced by drawing or stretching the bristles to increase the molecular orientation along the fiber axis. Therefore, it is preferred to stretch orient the filaments used to make the bristles of the present invention or to apply other standards property-enhancing processing to the techniques thereto.

10 Examples of other thermoplastic polymeric compositions from which the bristles of this invention may be formed include: polyolefins such as polyethylene and polypropylene; polyacrylics such as polyacrylonitrile, polyacrylamide, copolymers of acrylonitrile with methyl methacrylate, etc.; polyvinyl chloride and copolymers of vinyl chloride with other vinyl monomers, polymers of fluorinated
15 olefins such as polytetrafluoroethylene; polystyrene; and the like.

Additionally, the uniquely channeled cross-sectional shapes of the bristles of the present invention can be co-extruded from two or more distinct thermoplastic polymeric materials.

20

For example, a polybutylene terephthalate core can be co-extruded with a multi-channeled sheath of 6,12 nylon to produce a multi-channeled bristle that has a smaller diameter core than an extruded polybutylene terephthalate multi-channeled bristle. Such co-extruded multi-channeled bristles combine the best properties of
25 different thermoplastic polymeric materials to create co-extruded bristles with functional versatility including improved stiffness, softness, increased "packing", etc. Some of those are described in the Tynex® publication referenced above.

30 It is well known to those skilled in the art of toothbrush design and manufacture, that the bristle and its resulting "tuft" must possess certain optimum

- 27 -

characteristics commonly described, for example, as (a) softness, (b) flex strength, (c) recovery, (d) wet strength, (e) bendability, (f) permanent deformation, and others.

Typically, this requires balancing parameters such as (a) polymer type, (b) diameter of bristle (c) end rounding, (d) flagging, (e) extent of orientation during
5 bristle drawdown, (f) bristle length, and others.

It will be equally clear to those skilled in the art that similar commercial optimization is required for each of the novel bristle of this invention. In addition to
10 the parameters balanced when studying round bristle construction, one must additionally consider such parameters as, for example, (a) the dimensions of the "core" around which the channels are arranged, (b) the dimensions of the sides of the channels and (c) the internal dimensions of the channel itself. Generally, it is preferred that the channel depth is approximately 10 to 30% of the bristle diameter,
15 as measured at the maximum cross-section, where the channel breadth can vary from between about 10 to about 60% of the bristle diameter. In a particularly preferred embodiment of this invention, a penta-channel bristle having a maximum cross-section diameter of about 0.012 inches, has five channels with an average depth of about 0.003 inches and an average channel breadth at the center of the channel of
20 about 0.006 inches. See Figure 1 of the drawings.

The currently preferred embodiment of the bristle design of the present invention is a five-sided star shape bristle. While the five-sided star shape has been selected as the first commercial embodiment, due to its mouth-feel, clinical results,
25 and ability to withstand deformation or "wear-out" during a simulated one-to-three month wear test, it is anticipated that other star shapes will also prove to be commercially viable. Accordingly, it is anticipated that other bristle designs, e.g., 4, 5, 6, etc. sided stars (or other shapes) having dimensions which vary from that of the currently preferred embodiment will also prove useful in this invention.

- 28 -

One practical side-effect of providing the multi-channel bristles of this invention is that industry standards determined by experience over the years for round bristle parameters may need to be altered for channeled bristles. Thus, each channeled bristle should be optimized in its own right. For example, a round bristle
5 made of 6,12 nylon with a 0.008" diameter will exhibit certain desired commercial properties described as a "soft toothbrush, where as a channeled bristle may require a larger total diameter and careful attention to the "core" dimension or even a different polymer in order to achieve the same properties. This is illustrated in Table 2 below.

10

15

20

25

30

35

- 30 -

Polybutylene terephthalate bristles illustrative of the toothbrushes of the present invention are described in Table 3 below.

5

10

15

20

25

30

Table 3
Thermoplastic Polybutylene terephthalate Bristles

Bristle Shape	Trichannel	Tetrachannel (X)	Pentachannel	Hexachannel
Diameter (inch)	0.010	0.008	0.007	0.014
Channel Depth (inch)	0.003	0.0025	0.0025	0.002
Channel Breadth (inch)	0.006	0.0045	0.0040	0.003
Sp. Gravity (g/cc)	1.32	1.32	1.32	1.32
Tensile Strength (psi)	40-50	40-50	40-50	40-50
Tensile Elongation (%)	35-55	35-55	35-55	35-55
Melt Point (°F)	435	435	435	435
Dry Stiffness Modulus (psi)	320-365	320-365	320-365	320-365
Wet Stiffness Modulus (psi)	300-340	300-340	300-340	300-340

- 32 -

For the purposes of the present invention, abrasive is defined as traditional toothpaste abrasives as discussed in detail below, wherein the particle size (mean diameter) is between about 3 and about 25 microns.

5 Particularly preferred are abrasive mixtures where the secondary abrasive is the type used in translucent dentifrice gels at levels up to about 20%. Some of these mixtures are described in the following U.S. Patent Nos. 3,927,200; 3,906,090; 3,937,321; 3,911,102; 4,036,949; 4,891,211; 4,547,362; 5,374,368; 5,424,060; 5,180,576; 4,943,429; 4,160,022. Some of these mixed abrasives are commercially
10 available, e.g., Sylodent 15, Sylodent 2 (W.R. Grace), Aerosil 200 (Degussa) and Cabosil (Cabot).

 The size of the abrasive particles are most commonly expressed in "mean diameter" i.e., the arithmetical average of the diameters of particles in a
15 representative sample. The mean diameter value of abrasive particles is usually described in microns. Abrasives having particle sizes between about 3 and 25 microns and preferably between about 6 and about 20 microns are particularly preferred for the channel designs of the toothbrush bristles of the present invention.

20 The preparation of suitable particle size abrasives can be accomplished by conventional techniques well known to the art. Basically, these techniques involve milling various abrasive materials, followed by standard screen sieving (or air separation) to segregate the desired particle size range.

25 Preferred plaque and tartar fighting active ingredients that help control plaque and tartar buildup when included in a toothpaste are the surfactant/polydimethyl-siloxane hot melt emulsions commercially available under the trademark MICRODENT®. These are described in U.S. Patent Nos. 4,950,479 and 5,032,387. Particularly preferred plaque and tartar fighting active ingredients are surfactant/polydimethyl-
30 siloxane emulsions where the polydimethyl-siloxanes are high molecular weight

- 33 -

substances. Such surfactant -polydimethyl-siloxane emulsions are described in pending U.S. Patent Application Serial No. 08/144,778 and related applications. These are available commercially under the trademark ULTRAMULSION®. See Examples 6-9 below for improved methods of fighting tartar, plaque and stains
5 utilizing the toothbrush of the present invention with certain toothpastes that capitalize on the clean tooth surfaces obtained with the toothbrushes of the present invention.

The present invention will be further illustrated with reference to the following
10 examples which aid in the understanding of the present invention, but which are not to be construed as limitations thereof. All percentages reported herein, unless otherwise specified, are percent by weight. All temperatures are expressed in degrees Celsius.

15

20

25

- 34 -

EXAMPLE 1

In a crossover clinical toothbrushing study, patients brushed with a quadrachannel
bristle toothbrush and/or a contour rounded bristle toothbrush and then switched to
5 the other toothbrush. The ends of the bristles in these brushes are shown electron
micrographs in Figs. 9 and 10. Plaque scores were established before and after
brushing with each brush.

The results are reported in Table 4 below and in Figure 8. The CEC values for
10 this quadrachannel bristled brush were substantially greater than 1.5, i.e., about 2.59.
This was a statistically significant value with ($p = 0.001$), even with the small
number of subjects per cell.

15

20

25

- 35 -

Table 4

Data Summary of the Crossover Clinical Study						
Quadrachannel				Round		
Subject	Before	After	Difference	Before	After	Difference
02	2.20	0.82	1.38	2.29	1.88	0.41
03	1.85	0.63	1.22	2.26	1.62	0.64
04	1.58	0.57	1.01	1.96	1.40	0.56
06	1.60	0.55	1.05	1.83	1.36	0.47
07	2.30	1.73	0.57	2.30	1.97	0.33
09	2.06	1.26	0.80	1.94	1.82	0.12
10	2.03	0.99	1.04	1.79	1.78	0.01
11	2.19	1.20	0.99	2.27	1.84	0.43
12	2.49	1.16	1.33	1.79	1.78	0.01
13	2.09	1.48	0.61	2.37	2.05	0.32
14	3.67	2.00	1.67	3.38	2.21	1.17
Average	2.19	1.13	1.06	2.20	1.79	0.41
Std. Dev.	0.56	0.48	0.33	0.45	0.26	0.33
Min.	1.58	0.55	0.57	1.79	1.36	0.01
Max.	3.67	2.00	1.67	3.38	2.21	1.17

- 36 -

Examples 2 through 5

Examples 2 through 5 below are illustrative of various unique toothbrush/toothpaste embodiments of the present invention. These Examples are shown in Table 5 below.

- 37 -

Table 5

Example No.	2	3	4	5
Bristle Thermoplastic Polymeric Material	Polybutylene terephthalate	Polypropylene	Polybutylene terephthalate	Polyacrylonitrile
Bristle Shape	Hexachanneled	X-shaped	Cruciform	Pentachannel
No. of Bristles/Tuft and No. of Tufts in Toothbrush Head	6/20	8/30	4/15	10/24
Particle size of toothpaste abrasive in microns	3-6	6-20	3-25	6-18
CEC in %	10	65	30	70
Antiplaque/ Anti-tartar Active ingredient/and mol. wt. of polydimethylsiloxane	MICRODENT® 12,000	MICRODENT® 1500	ULTRA-MULSION® 2.5 million cs	ULTRA-MULSION® 50 million cs

- 38 -

Examples 6-9

Using standard toothpaste formulating procedures such as those taught in U.S. Patent No. 4,254,101, the ULTRAMULSION® containing toothpastes identified
5 below in Table 6 were prepared. All percentages reported below are percent by weight. PDMS is an abbreviation for polydimethyl-siloxane.

10

15

20

25

- 39 -

Table 6

ULTRAMULSION® Toothpaste					
Example No.	6	7	8	9	
5	<hr/>				
	Ingredients (wt. %):				
	Deionized Water	16.87	30.44	43.76	16.87
	Sorbitol-70% Aq.	18	24.6	20	18
	Glycerin	10	8	10	10
10	Dicalcium Phosphate	49	x	x	49
	Aluminum Oxide	x	10	x	x
	Hydrated Silica	x	20	19	x
	Cellulose Gum	1	0.8	x	1
	Xanthan Gum	x	x	0.9	x
15	Sodium Monofluoro Phosphate	0.76	0.76	0.76	0.76
	Titanium Dioxide	0.5	0.4	0.6	0.5
	Sodium Saccharin	0.27	0.2	0.28	0.27
	PEG-8	x	1	0.8	x
20	Flavor	0.8	1	0.9	0.8
	Sodium Lauryl Sulfate	0.8	0.8	1	0.8
	ULTRAMULSION (2,500,000 cs PDMS)	2	x	x	x
25	ULTRAMULSION (50,000,000 cs PMDS)	x	2	x	x
	ULTRAMULSION (12,500 cs PMDS)	x	x	2	x
	ULTRAMULSION (1,500 cs PMDS)	x	x	x	2
30	TOTAL	100	100	100	100

- 40 -

Example 10

Comparison of Penta-Channeled Bristles of Varying
Channel Depth With Round Bristles (polybutylene terphthalate)

5

Clinical Protocol:

Nineteen subjects, screened for good oral health were instructed to refrain from brushing for 24 hours. The plaque of each subject was stained and scored for
10 Plaque utilizing a standard method (Turesky modification of Quigley-Hein). The subjects then took their assigned brush and assigned toothpaste (Colgate[®] Fluoride Toothpaste) and brushed without benefit of a mirror for one minute, after which they were re-stained and residual plaque was re-scored using the same Index. Each of the
15 control. Between trials the subjects returned to their normal oral hygiene habits, assuring a constant return to baseline.

All toothbrushes tested were identical in shape, number and placement of bristles and by the naked eye, appeared to be completely identical. Only microscopic
20 examination of the bristles for the presence of channels could disclose a difference. The toothbrush shape selected for this trial was the very popular "diamond head" shape commercially available as Colgate Plus[®] and numerous private label brands.

Results:

25 As shown in Table 7 below, there is a dramatic difference in plaque removal comparing the channeled bristle to the round bristle. There is likewise a distinct correlation between channel depth and relative plaque removal. These differences are statistically significant ($p \leq 0.0001$) after a single brushing. Although both penta-channeled bristle designs were effective, these data suggest that the deeper the
30 channel, the greater the effectiveness on cleaning.

Table 7

Comparison of Pentachannel Bristles of Varying Depth
With Round Bristles (polybutylene terphthalate)

	ROUND	PENTACHANNEL (1)	PENTACHANNEL (2)
Outside diameter (inch)	0.007	0.007	0.007
CHANNEL DEPTH (inch)	-0-	0.0012	0.0009
PLAQUE INDICES (Std. Dev.)			
INDEX	Before Brushing	After Brushing	Before Brushing After Brushing
Whole Mouth	2.28 (0.27)	1.81 (0.27)	2.21 (0.5) 1.04 (0.44)
Proximal Surfaces	2.40 (0.24)	1.99 (0.28)	2.38 (0.11) 1.13 (0.12)
Posterior Surfaces	2.43 (0.23)	1.94 (1.94)	2.29 (0.41) 1.14 (0.47)
Smooth Surfaces	2.04 (0.32)	1.45 (0.27)	1.87 (0.57) 0.88 (0.35)
			2.03 (0.37) 0.74 (0.30)

(1) There was no statistical differences between the "Before Brushing" means for any bristle shape using any of the reported Indices. (ANOVA)

(2) Underlined means are statistically significant ($p < 0.0001$) from their ROUND "After Brushing" cohort. (paired t-test)

- 42 -

Example 11

5 Comparison of Round Bristles of Two Polymer Types
With Pentachanneled Bristles

10 This protocol was identical to the previous Example except that there were
five (5) subjects using the round nylon bristle and the pentachannel PBT bristle in
this trial. The toothbrushes were also of the same construction as in Example 10 and
not discernibly different to the naked eye.

15 The results comparing a nylon round bristle, a PBT round bristle and a PBT
pentachannel bristle are set out in Table 8 below. The column of data for the round
PBT bristle is the same as in the previous Example. In spite of the disparity in the
number of subjects tested, the statistical significance remained and this experiment
clearly indicates that it is the presence of the channels which contributes to the
greater removal of plaque in a single brushing, whereas the polymer selected for
manufacturing the bristle did not produce a comparable effect on the plaque
20 removing properties.

25 However, standard wear tests of various bristles suggest that channeled bristle
toothbrushes constructed of polybutylene terephthalate are preferred over comparably
channeled bristle toothbrushes constructed of nylon (TYNEX®).

Table 8

Comparison of Two Round Bristle Types with One Pentachannel Bristle Type

	NYLON (TYNEX®)	PBT'	PBT'
	ROUND	ROUND	PENTACHANNEL
Outside diameter (in)	0.007	0.007	0.007
CHANNEL DEPTH(in)	-0-	-0-	0.001
WHOLE MOUTH PLAQUE INDEX'' (Std. Dev.)			
	Before Brushing	After Brushing	Before Brushing After Brushing
	2.14 (0.10)	1.79(0.06)	2.28 (0.27) 1.81(0.27) 2.17 (0.13) <u>0.95(0.18)</u>

Footnotes:

1. 'PBT = polybutylene terephthalate.
2. '' PLAQUE INDEX = Turesky modification of Quigley Hein.
3. Underlined mean was statistically significant ($p < 0.0006$) difference when compared to either "After Brushing" with round bristles. (unpaired t-test)
4. There was no statistical significance between any "Before Brushing" means. (ANOVA)

- 44 -

The present invention has been described in detail, including the preferred embodiments thereof. However, it will be appreciated that those skilled in the art, upon consideration of the present disclosure, may make modifications and/or improvements on this invention and still be within the scope and spirit of this
5 invention as set forth in the following claims.

10

15

20

25

- 45 -

WHAT IS CLAIMED IS:

1. A toothbrush having improved cleaning efficiency, wherein the toothbrush bristles are composed of a synthetic thermoplastic polymeric composition and comprise a multiplicity of groups of multichanneled bristles, wherein lateral surfaces of said bristles contain at least two longitudinal channels extending along the length of said bristles, said channels having a depth sufficient to entrap a quantity of toothpaste abrasive, having an average particle size between about 3 and about 25 microns; wherein the cleaning and abrasion contact between said quantity of abrasive entrapped in said channels and the surfaces of the teeth is improved during brushing, resulting in a cleaning efficiency coefficient of at least about 1.5 and an abrasion efficiency coefficient of at least about 1.5.
2. A toothbrush according to claim 1, wherein the lateral surface of said bristles comprise from between about 3 and 8 channels extending substantially the length of the bristles.
3. A toothbrush according to claim 2, wherein said bristles have cross-sectional configurations as illustrated in Figures 2, 3 and 4 of the drawings accompanying this specification.
4. A toothbrush according to claim 2, wherein the cross-sectional configuration of said bristles comprises three or more channels, shaped to readily accept a quantity of abrasive having an average particle size between about 6 and about 20 microns.
5. A toothbrush according to claim 1, wherein the bristles have a diameter between about 0.008 and 0.014 inches, a channel depth between about 0.002 and 0.005 inches and a channel breadth between about 0.003 and 0.006 inches.
6. A toothbrush according to claims 1, wherein the bristles interlock

- 46 -

during brushing.

7. A toothbrush according to claim 1, having a cleaning efficiency coefficient of at least about 2.0 and an abrasion efficiency coefficient of at least about 2.0.

8. A toothbrush according to claim 1, wherein the bristle tips are flagged.

9. A toothbrush according to claim 1, wherein the bristles are formed by melt extruding a synthetic thermoplastic polymeric composition selected from the group consisting of synthetic linear condensation polyamides, polyolefins, polyacrylics, polyacrylamides, copolymers of acetonitrile with methyl methacrylate, polyvinyl chloride, copolymers of vinyl chloride with other vinyl monomers, polymers of fluorinated olefins and polystyrene.

10. A toothbrush according to claim 9, wherein the bristles are formed by melt extruding nylon.

11. A toothbrush according to claim 9, wherein the bristles are formed by melt extruding polybutylene terephthalate.

12. A toothbrush according to claim 9, wherein the synthetic polyamide is Nylon 6,12.

13. A toothbrush according to claim 9, wherein the synthetic polyamide is Nylon 6,6.

14. A toothbrush according to claim 9, wherein the synthetic polyamide is Nylon 6.

- 47 -

15. A toothbrush according to claim 1, wherein the abrasion efficiency coefficient values for one or more of RDA, Stain Index and Polishing Index are above about 1.5.

16. A method of gently cleaning teeth and soft tissue in the oral cavity comprising brushing with an abrasive containing substance in combination with a toothbrush having improved cleaning efficiency and abrasion efficiency, wherein:

- (a) the average particle size of said abrasive is between about 3 and about 25 microns,
- (b) said toothbrush comprises a multiplicity of groups of multi-channeled bristles, wherein lateral surfaces of said bristles contain at least two longitudinal channels extending substantially along the longitudinal length of each bristle, with said channels of a depth sufficient to entrap an effective quantity of said abrasive, and
- (c) the contact between said abrasive entrapped in said channels and surfaces of the teeth is improved during brushing, resulting in a cleaning efficiency coefficient of at least about 1.5 and an abrasion efficiency coefficient of at least about 1.5, without adversely effecting the soft tissue in the oral cavity.

17. A method of manufacturing a toothbrush having improved cleaning and abrasion efficiency, comprising securing several bundles of multi-channeled bristles to a conventional toothbrush head/handle arrangement, wherein the lateral surfaces of said bristles contain at least two longitudinally extending channels substantially along the length of said bristles, with said channels having a depth sufficient to entrap an effective quantity of abrasive, said abrasive having an average particle sizes between about 3 and about 25 microns, whereby the use of said toothbrush during brushing resulting in a cleaning efficiency coefficient of at least about 1.5 and an abrasion efficiency coefficient of at least about 1.5.

- 48 -

18. A method according to claim 17, wherein said lateral surfaces of said bristles are quadrachannel shaped to readily deliver effective quantities of said abrasive to the surfaces of the teeth, gums and tongue during brushing.

19. An improved method of cleaning tooth and soft tissue surfaces in the mouth comprising brushing said surfaces with toothbrush bearing an abrasive based toothpaste containing a plaque fighting active ingredient comprising an emulsion of a polydimethyl-siloxane in a nonionic poloxamer surfactant, and wherein the toothbrush comprises multichanneled abrasive entrapping bristles and contact between said abrasive and said tooth and soft tissue surfaces during brushing is improved over conventional nonchanneled bristle toothbrushes, with an improved cleaning efficiency coefficient of at least about 1.5 and an abrasion efficiency coefficient of at least about 1.5.

20. An improved method of mechanically cleansing plaque, tartar, stains, and *materia alba* from tooth surfaces in the mouth while avoiding gingival abrasion and protecting the base of the gingival sulcus comprising brushing said tooth surfaces with toothbrush bearing an abrasive based toothpaste containing a plaque fighting active ingredient comprising an emulsion of a polydimethyl-siloxane in a nonionic poloxamer surfactant, and wherein the toothbrush comprises multichanneled abrasive entrapping bristles and contact between said abrasive and said tooth surfaces during brushing is improved over conventional nonchanneled bristle toothbrushes, with an improved cleaning efficiency coefficient of at least about 1.5 and an abrasion efficiency coefficient of at least about 1.5.

21. An improved method of mechanically cleansing teeth with an abrasion wiping action wherein a toothbrush with abrasive entrapping multi-sided, channeled bristles is used in combination with a toothpaste containing abrasive having an average particle size between about 3 and 25 microns, the use of said toothbrush and

- 49 -

toothpaste resulting in an improved cleaning efficiency coefficient of at least about 1.5 and an abrasion efficiency coefficient of at least about 1.5.

22. A method of enhancing the cleaning of tooth surfaces contiguous to the gingival margin and to interproximal surfaces comprising; combining an abrasive based toothpaste with a toothbrush containing a multiplicity of multi-channeled bristles, wherein the lateral surfaces of said bristles contain channels extending substantially the length thereof, said channels having a depth sufficient to entrap an effective cleansing amount of abrasive particles having an average particle size of between about 1 and 25 microns, such that the contact between said entrapped abrasive and tooth surfaces resulting in an improved cleaning efficiency coefficient of at least about 1.5 and an abrasion efficiency coefficient of at least about 1.5.

23. A toothbrush having improved cleaning efficiency, said toothbrush comprising a multiplicity of bristles wherein lateral surfaces of said bristles contain at least one longitudinal channel extending along the length of said bristles, said channels having a depth sufficient to entrap toothpaste abrasive having a particle size between about 1 and about 7 microns; wherein the contact between said abrasive entrapped in said channels and surfaces of the teeth is improved during brushing, resulting in a cleaning efficiency coefficient, CEC, from between about 20% and about 90%.

24. A toothbrush according to claim 23, wherein the lateral surface of said bristles comprise a multiplicity of channels extending the entire length of the bristles.

25. A toothbrush according to claim 24, wherein said bristle channels are selected from trichannel, quadrachannel, pentachannel, hexachannel and heptachannel configurations in cross-section, or combinations thereof.

26. An improved method of treating hypersensitive teeth in the oral cavity

- 50 -

comprising brushing teeth and gums with a tubule blocking active ingredient contained in a toothpaste in combination with a toothbrush having improved hypersensitivity treating and cleaning efficiency wherein:

- (A) the active ingredient is selected from the group consisting of potassium nitrate, potassium oxalate, stannous fluoride and zirconium chlorides and abrasives and mixtures thereof,
- (B) said toothbrush comprises a multiplicity of groups of multi-sided bristles, wherein lateral surfaces of said bristles contain at least one longitudinal channel-extending along the length of said bristles, with said channels of a depth sufficient to entrap said active ingredient, and
- (C) the contact between said active ingredient entrapped in said channels and the surfaces of the teeth including those tubules responsible for hypersensitivity is improved during brushing resulting in improve active-ingredient treatment of the hypersensitive tubules, said toothbrush further providing an improved cleaning efficiency coefficient of at least about 1.5 and an abrasion efficiency coefficient of at least about 1.5, in comparison to round bristle toothbrushes.




FIG. 1A




FIG. 1B




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 5




FIG. 8

3/5




FIG. 6





FIG. 7



FIG. 9



BEST AVAILABLE COPY




FIG. IIA




FIG. IIB

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US97/12206

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :A46B 9/04; A61C 17/00

US CL :15/167.1, 207.2; 300/21; 433/216; 428/397, 401

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 15/167.1, 207.2; 300/21; 433/216; 428/397, 401

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONEElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)
NONE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X -- Y	US 2,876,477 A (STEWART) 10 March 1959, see entire document.	1-4,6,7,9, 10,15,17 ----- 5,8,11-14, 16
X -- Y	US 3,238,553 A (BAILEY ET AL) 08 March 1966, see entire document.	1-4,6,7,9, 10,15,17 ----- 5,11-14
Y	GB 897,404 A (E.I. DU PONT DE NEMOURS AND COMPANY) 30 May 1962, see entire document.	8
A	US 3,302,230 A (POPPELMAN) 07 February 1967.	1-17



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	"T"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"B" earlier document published on or after the international filing date	"Y"	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"A"	document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means		
"P" document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

16 OCTOBER 1997

Date of mailing of the international search report

02 DEC 1997

Name and mailing address of the ISA/US

Authorized officer *J. Hurd*

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/12206

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3,302,230 A (POPPELMAN) 07 February 1967.	1-17
A	US 3,344,457 A (GROBERT) 03 October 1967.	1-15,17
A	US 4,927,281 A (GUERET) 22 May 1990.	1-15,17
A	US 5,020,551 A (GUERRET) 04 June 1991.	1-15,17

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ BLACK BORDERS

☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☐ FADED TEXT OR DRAWING

☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☒ SKEWED/SLANTED IMAGES

☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☐ LINES OR MARKS ON ORIGINAL DOCUMENT

☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)